



Anglo Adhesives & Services Ltd.

INDUSTRIAL ADHESIVE MANUFACTURERS - CONTRACT FILLING AND PACKAGING

Anglo House The Airfield Dalby Road Melton Mowbray Leicestershire LE13 0BL UK

Tel: +44(0)1664 480866 - Fax: +44(0)1664 480963

E-mail: sales@anglo-adhesives.co.uk Web: www.anglo-adhesives.co.uk



TECHNICAL DATA SHEET

PRODUCT	SOLIBOND 4317J								
DESCRIPTION	General-purpose solvent based clear adhesive.								
SPECIFICATION	<table><tr><td>% Non Volatiles, w/w</td><td>30 to 40</td></tr><tr><td>Viscosity, Brookfield RVT, Spindle 3, Speed 20, °C</td><td>850-1350cps</td></tr><tr><td>Appearance</td><td>Clear, mobile liquid</td></tr><tr><td>Weight per litre</td><td>0.790-0.830Kg</td></tr></table>	% Non Volatiles, w/w	30 to 40	Viscosity, Brookfield RVT, Spindle 3, Speed 20, °C	850-1350cps	Appearance	Clear, mobile liquid	Weight per litre	0.790-0.830Kg
% Non Volatiles, w/w	30 to 40								
Viscosity, Brookfield RVT, Spindle 3, Speed 20, °C	850-1350cps								
Appearance	Clear, mobile liquid								
Weight per litre	0.790-0.830Kg								
CLEANER	Solibond PS100								
APPLICATION	<p>Ensure both surfaces are clean, dry and free from grease. Depending on the nature of the surfaces to be bonded, adhesive should be applied to one or both surfaces.</p> <p>On non-porous surfaces, apply a thin even layer of adhesive to both surfaces, leave to dry for approximately 10 minutes before pressing together firmly.</p> <p>On porous surfaces apply a generous coat to one surface then press together.</p>								
SHELF LIFE	12 months when stored in dry conditions in unopened container between 5 and 30°C. Do not store near heat source.								

Issue Number: 1
Revision Number: -
Revision Date: 18th December 2006
Revision Comments: New product



Registered In England & Wales. No. 3842448
Directors: Peter C. Kinder (Managing), Charlotte O. Davey (Sales and Marketing)
Part of the Anglo Adhesives & Services Group incorporating:
Crispin Adhesives Ltd - Howlett Adhesives Ltd & Fosse Polymers Products Ltd.

